

WHAT IS CLAIMED IS:

1. A stabproof and bulletproof panel, comprising:

a bulletproof panel comprised of,

5 a front plate 45 consisting of,

a plurality of aromatic polyamide woven fabrics 41,

10 a felt 50 formed by forcibly inserting thin aromatic
polyamide fibers or high density polyethylene
fibers 52 and a shock-absorbing member 51 into a
scrim woven in the form of a net using aromatic
polyamide fibers or high density polyethylene
yarn, and

a plurality of aromatic polyamide woven fabrics 43,

15 a plurality of high density polyethylene films 44
stacked with one on top of another for dispersing
impact energy, and

a rear plate 46 formed by sewing together a plurality
of aromatic polyamide woven fabrics for minimizing
frictional heat and deformation; and

20 five to twelve stabproof panels 60 brought into tight
contact with the front surface of said bulletproof
panel 40.

2. The stabproof and bulletproof panel according to claim
25 1, wherein said stabproof panel 60 is constructed by spreading

10992694 1001
a resinous bonding agent 61 on one surface of an aromatic
polyamide woven fabric 41, high density polyethylene woven
fabric or similar high strength woven fabric and, thereafter,
projecting sands 62, each of which has a particle size
5 corresponding to the particle size of a No. 100 to 500 sand
paper, to the resinous bonding agent 61 to densely bond sands
62 on the surface.

3. The stabproof and bulletproof panel according to claim
10 1 or 2, wherein said stabproof panel 60 is composed of 60 to
65 wt % of the aromatic polyamide woven fabric 41, high
density polyethylene woven fabric or similar high strength
woven fabric, 1 to 2 wt % of the resinous bonding agent 61 and
35 to 40 wt % of the sands.